crevin

5 years guarantee

General Information



Composition 54%PES 46%PES REC

Width 140 + 4cm

Weight

 $470 \text{ gr/m} 2 \pm 5 \%$ $658 \, \text{gr/lm} \pm 5 \, \%$

Custom code UE: 5801.36.00

IN-01441/2010 805.179/07/09

USA: 5801.36.00.20 Laboratory test number **Specifications**

Seam slippage resistance (mm)

Warp: 1,90 Weft: 1,80

EN ISO 13936/2:2004

Abrasion resistance (End point)

>100.000 EN ISO 12947-2:1998

Abrasion resistance (change of aspect: 3000 cycles)

3-4 EN ISO 12947/4:1998 and EN 14465:2003 (Annex A)

Pilling resistance

4-5 EN ISO 12945/2:2000

Lightfastness

4-5 EN ISO 105-B02:1998

Care

PERFORMANCE+

Easy to clean, longlasting fabrics

Washing conditions







Soiling and cleanability

4-5 FORD FLTM BN 112-08:2005

Dimensional change domestic washing and drying (%)

Warp: -1,5 Weft: <u>-1,5</u>


and EN ISO 5077:2008

When confectioning or washing the sofa cover with velcro please attach a protective cloth.

Ignitability

BS5852 Source 0 EN1021-Part 1:2006 CAL TB 117:2013 NFPA 260:2013

Environmental considerations



46% GRS recycled PET bottles **54% PES**

Life cycle analysis

Cradle to gate assessment. From raw material extraction to finished fabric: resources, yarn production and dyeing, fabric weaving and finishing, waste recycling.

Carbon footprint

 $348 \, {\rm kg\,CO_2\,eq/m} \atop {\rm 22,49\%\,less\,since\,2020}$

Water consumption

71,57 liters/m 24,37% less since 2020



UNIVERSITAT POLITÈCNICA DE CATALUNYA BARCELONATECH

Escola Superior d'Enginyeries Industrial, Aeroespacial i Audiovisual de Terrassa

Study realized in collaboration with UPC

Methodology:

Life Cycle Analysis. ISO 14040 standard.

Own data, Ecoinvent 3.6 database and published data.

1 linear meters, 140 cm width.

Calculation methodology: ReCiPe Midpoint (H) 2016 v1.0

ReCiPe Endpoint (H) 2016 v1.04 IPCC 2013 GWP 100a v1.03

Designed and Crafted in Terrassa (Barcelona)

Certificates











