






5 years guarantee • sanitized (antimicrobial)

| General Information | Specifications | Care | | |
|--|---|--|---|--|
|  <p>Composition 34%PP 32%PES 21%PES REC 7%CO REC 6%OF REC</p> <p>Width 140 + 4cm</p> <p>Weight 536 gr/m² ± 5 % / 750 gr/lm ± 5 %</p> <p>Custom code UE: 5801.36.00 USA: 5801.36.00.20</p> <p>Laboratory test number IN-01458-2016-B-2 2020AN1320 EN ISO 20743</p> | <p>Seam slippage resistance (mm) Warp: <u>2.00</u> Weft: <u>2.20</u> EN ISO 13936/2:2004</p> <p>Abrasion resistance (End point) 60.000 EN ISO 12947-2:1998</p> <p>Abrasion resistance (change of aspect: 3000 cycles) <u>4</u> EN ISO 12947/4:1998 and EN 14465:2003 (Annex A)</p> <p>Pilling resistance <u>4-5</u> EN ISO 12945/2:2000</p> <p>Lightfastness <u>5-6</u> EN ISO 105-B02:1998 and 105 B02/A01:2002</p> | <p>Care</p> <p>PERFORMANCE+ Easy to clean, longlasting fabrics</p> <p>Washing conditions </p> <p>Soiling and cleanability <u>4-5</u> FORD FLTM BN 112-08:2005</p> <p>Dimensional change domestic washing and drying (%) Warp: <u>-2</u> Weft: <u>-2</u> EN ISO 3759:2008, EN ISO 6330:2000 and EN ISO 5077:2008</p> <p>When confectioning or washing the sofa cover with velero please attach a protective cloth.</p> <p>Antibacterial activity Strong antibacterial property >3 EN ISO 20743:2013</p>  <p>Ignitability</p> <table border="0"> <tr> <td>BS5852 Source 0 EN1021-Part 1:2006 CAL TB 117:2013 NFPA 260:2013</td> <td>Upon Request: BS5852 Source 1 EN1021-Part 2:2006 BS 7176 Low Hazard UNI 9175 Clase 3IM</td> </tr> </table> | BS5852 Source 0 EN1021-Part 1:2006 CAL TB 117:2013 NFPA 260:2013 | Upon Request: BS5852 Source 1 EN1021-Part 2:2006 BS 7176 Low Hazard UNI 9175 Clase 3IM |
| BS5852 Source 0 EN1021-Part 1:2006 CAL TB 117:2013 NFPA 260:2013 | Upon Request: BS5852 Source 1 EN1021-Part 2:2006 BS 7176 Low Hazard UNI 9175 Clase 3IM | | | |

Environmental considerations

| | | |
|--|--|---|
|  <p>21% GRS recycled PET bottles 7% Recycled CO 6% Circular yarn from own waste 34% Low impact yarn (PP) 32% PES</p> | <p>Life cycle analysis Cradle to gate assessment. From raw material extraction to finished fabric: resources, yarn production and dyeing, fabric weaving and finishing, waste recycling.</p> <p>Carbon footprint 3,9 kg CO₂ eq / m 15,03% less since 2020</p> <p>Water consumption 95,65 liters / m 28,24% less since 2020</p> |  <p>UNIVERSITAT POLITÈCNICA DE CATALUNYA BARCELONATECH Escola Superior d'Enginyeries Industrial, Aeroespacial i Audiovisual de Terrassa</p> <p>Study realized in collaboration with UPC</p> <p>Methodology: Life Cycle Analysis. ISO 14040 standard.</p> <p>Database: Own data, Ecoinvent 3.6 database and published data.</p> <p>Functional unit: 1 linear meters, 140 cm width.</p> <p>Calculation methodology: ReCiPe Midpoint (H) 2016 v1.0 ReCiPe Endpoint (H) 2016 v1.04 IPCC 2013 GWP 100a v1.03</p> |
|--|--|---|

Designed and Crafted in Terrassa (Barcelona)

Certificates

