

5 years guarantee • fire resistant

General Information	Specifications	Care
 Composition 44%PET REC 35%PP 11%MA 6%CO REC 4%PES Width 140 + 4cm Weight 668 gr/m2 ± 5 % 935 gr/lm ± 5 % Custom code UE: 5801.36.00 USA: 5801.36.00.20 Laboratory test number IN-00662-2025-1	Seam slippage resistance (mm) Warp: 1,7 Weft: 1,7 EN ISO 13936/2:2004 Abrasion resistance (End point) 60.000 EN ISO 12947-2:1998 Abrasion resistance (change of aspect: 3000 cycles) 4 EN ISO 12947/4:1998 and EN 14465:2003 (Annex A) Pilling resistance 5 EN ISO 12945/2:2000 Lightfastness ≥6 EN ISO 105-B02:1998 and 105 B02/A01:2002 Colour fastness to rubbing Dry: 4-5 Wet: 4-5 EN ISO 105-X12:2002	PERFORMANCE+ Easy to clean, longlasting fabrics Washing conditions