











easy stain release

General Information	Specifications	Care
<div></div> <div><b>Composition</b> 53%PET REC 34%PP 7%CO REC 6%OF REC</div> <div><b>Width</b> 140 + 4cm</div> <div><b>Weight</b> 568 gr/m2 ± 5 % 795 gr/lm ± 5 %</div> <div><b>Custom code</b> UE: 5407.73.00 USA: 5407.73.20.60</div> <div><b>Laboratory test number</b> IN-000947/2025-1</div>	<div><b>Seam slippage resistance (mm)</b> Warp: 2,3 Weft: 2,3 EN ISO 13936/2:2004</div> <div><b>Abrasion resistance (End point)</b> 50.000 EN ISO 12947-2:2016</div> <div><b>Abrasion resistance (change of aspect: 3000 cycles)</b> 3-4 EN ISO 12947/4:1998 and EN 14465:2003 (Annex A)</div> <div><b>Pilling resistance</b> 4 EN ISO 12945/2:2000</div> <div><b>Lightfastness</b> &gt;6 EN ISO 105-B02:1998 and 105 B02/A01:2002</div> <div><b>Colour fastness to rubbing</b> Wet: 4-5 Dry: 4-5 EN ISO 105-X12:2002</div> <div><b>Notes:</b> Ito is woven with a bouclé yarn that creates a natural, irregular surface effect. Bouclé fabrics are generally more sensitive to wear effects than flat wovens, and with intensive or prolonged use may take on a more pronounced texture.</div>	<div><b>Washing conditions</b> </div> <div><b>Soiling and cleanability</b> 3 FORD FLTm BN 112-08:2005</div> <div><b>Dimensional change domestic washing and drying (%)</b> Warp: -3% Weft: -2% EN ISO 3759:2008, EN ISO 6330:2000 and EN ISO 5077:2008</div> <div>Bleach cleanable 80% water 20% bleach. In case of mould growth, machine-wash with a mild laundry detergent and add 0,2 liter of household bleach to the first rinse cycle. Wash at 40°C during at least 30 minutes. Use gentle cycle with minimal centrifugation.</div> <div>When confectioning or washing the sofa cover with velcro please attach a protective cloth.</div>
		<div><b>Ignitability</b>  BS5852 Source 0 EN1021-Part 1:2006 CAL TB 117:2013 NFPA 260:2013</div>

Environmental considerations		
<div><div>66% recycled yarn</div></div> <div>53% GRS recycled PET bottles 7% Recycled CO 6% Circular yarn from own waste 34% Low impact yarn (PP)</div>	<div><b>Life cycle analysis</b> Cradle to grave assessment. From raw material extraction to end of use scenarios (75% Landfilling – 20% Incineration – 5% Recycling): Resources, yarn production and dyeing, fabric weaving and finishing, waste recycling, daily use and end of live.</div> <div><b>Carbon footprint</b> 5,05 kg CO<sub>2</sub> eq /m</div> <div><b>Water consumption</b> 164,26 liters/m</div>	<div><div>UNIVERSITAT POLITÈCNICA DE CATALUNYA BARCELONATECH</div><div>Escola Superior d'Enginyeries Industrial, Aeroespacial i Audiovisual de Terrassa</div></div> <div><div>Study realized in collaboration with UPC</div><div>Methodology: Life Cycle Analysis. ISO 14040 standard.</div><div>Database: Own data, Ecoinvent 3.6 database and published data.</div><div>Functional unit: 1 linear meters, 140 cm width.</div><div>Calculation methodology: ReCiPe Midpoint (H) 2016 v1.0 ReCiPe Endpoint (H) 2016 v1.04 IPCC 2013 GWP 100a v1.03</div></div> <div><div>Usage scenario: 1 home wash per year 1 vacuum per month For 15 years</div><div>End-of-life scenario: 75% Landfill 20% Incineration 5% Recycling</div></div>

<div>Designed and Crafted in Terrassa (Barcelona)</div>	<div>Certificates</div> <div></div>
---	---