


5 years guarantee • fire resistant

General Information	Specifications	Care		
 Composition 44%PET REC 35%PP 11%MA 6%CO REC 4%PES Width 140 + 4cm Weight 668 gr/m2 ± 5 % 935 gr/lm ± 5 % Custom code UE: 5801.36.00 USA: 5801.36.00.20 Laboratory test number IN-00662-2025-1	Seam slippage resistance (mm) Warp: 1,7 Weft: 1,7 EN ISO 13936/2:2004 Abrasion resistance (End point) 60.000 EN ISO 12947-2:2016 Abrasion resistance (change of aspect: 3000 cycles) 4 EN ISO 12947/4:1998 and EN 14465:2003 (Annex A) Pilling resistance 5 EN ISO 12945/2:2000 Lightfastness >6 EN ISO 105-B02:1998 and 105 B02/A01:2002 Colour fastness to rubbing Dry: 4-5 Wet: 4-5 EN ISO 105-X12:2002	PERFORMANCE+ Easy to clean, longlasting fabrics Washing conditions  Soiling and cleanliness 4 FORD FLTM BN 112-08:2005 Dimensional change domestic washing and drying at 30° (%) Warp: -3% Weft: -3% EN ISO 3759:2008, EN ISO 6330:2000 and EN ISO 5077:2008 *Dimensional change domestic washing and drying at 40° (%) Warp: -4% Weft: -4% EN ISO 3759:2008, EN ISO 6330:2000 and EN ISO 5077:2008 When confectioning or washing the sofa cover with velcro please attach a protective cloth. Ignitability<table><tr><td>BS5852 Source 0 EN1021-Part 1:2006 CAL TB 117:2013 NFPA 260:2013</td><td>BS5852 Source 1 EN1021-Part 2:2006 BS 7176 Low Hazard UNI 9175 Clase 3IM</td></tr></table>	BS5852 Source 0 EN1021-Part 1:2006 CAL TB 117:2013 NFPA 260:2013	BS5852 Source 1 EN1021-Part 2:2006 BS 7176 Low Hazard UNI 9175 Clase 3IM
BS5852 Source 0 EN1021-Part 1:2006 CAL TB 117:2013 NFPA 260:2013	BS5852 Source 1 EN1021-Part 2:2006 BS 7176 Low Hazard UNI 9175 Clase 3IM			

Environmental considerations

 44% GRS recycled PET bottles 6% Recycled CO 35% Low impact yarn (PP) 11% MA 4% PES	Life cycle analysis Cradle to gate assessment. From raw material extraction to finished fabric: resources, yarn production and dyeing, fabric weaving and finishing, waste recycling. Carbon footprint 4,91 kg CO₂ eq/m Water consumption 133,47 liters/m	UNIVERSITAT POLITÈCNICA DE CATALUNYA BARCELONATECH Escola Superior d'Enginyeries Industrial, Aeroespacial i Audiovisual de Terrassa Study realized in collaboration with UPC Methodology: Life Cycle Analysis. ISO 14040 standard. Database: Own data, Ecoinvent 3.6 database and published data. Functional unit: 1 linear meters, 140 cm width. Calculation methodology: ReCiPe Midpoint (H) 2016 v1.0 ReCiPe Endpoint (H) 2016 v1.04 IPCC 2013 GWP 100a v1.03
--	--	--

Designed and Crafted in Terrassa (Barcelona)	Certificates 
--	---