



outdoor • waterproof • easy stain release • bleach cleanable • fire resistant

General Information	Specifications	Care
 Composition 70%PP 11%MA 9%PET REC 6%COREC 4%PU Width 140 + 4cm Weight 692 gr/m2 ± 5 % 970 gr/lm ± 5 % Custom code UE: 5903.20.90 USA: 5903.20.18.00 Laboratory test number IN-000946/2025-1	Seam slippage resistance (mm) Warp: 2,8 Weft: 2,8 EN ISO 13936/2:2004 Abrasion resistance (End point) 50.000 EN ISO 12947-2:2016 Abrasion resistance (change of aspect: 3000 cycles) 4 EN ISO 12947/4:1998 and EN 14465:2003 (Annex A) Pilling resistance 4-5 EN ISO 12945/2:2000 Lightfastness to weather ≥6 EN ISO 105-B04:1997 (1000 hours) Colour fastness to rubbing Wet: 4-5 Dry: 4-5 EN ISO 105-X12:2002	Washing conditions  Soiling and cleanability 4 FORD FLTM BN 112-08:2005 Dimensional change domestic washing and drying (%) Warp: -3% Weft: -1% EN ISO 3759:2008, EN ISO 6330:2000 and EN ISO 5077:2008 Bleach cleanable 80% water 20% bleach. In case of mould growth, machine-wash with a mild laundry detergent and add 0,2 liter of household bleach to the first rinse cycle. Wash at 40°C during at least 30 minutes. Use gentle cycle with minimal centrifugation. When confectioning or washing the sofa cover with velcro please attach a protective cloth.
		Ignitability BS5852 Source 0 EN1021-Part 1:2006 CAL TB 117:2013 NFPA 260:2013 BS5852 Source 1 EN1021-Part 2:2006 BS 7176 Low Hazard UNI 9175 Clase 3IM IMO Anexo 1 Parte 8
Environmental considerations		
 15% recycled yarn 9% GRS recycled PET bottles 6% Recycled CO 70% Low impact yarn (PP) 11% MA 4% PU	Life cycle analysis Cradle to gate assessment. From raw material extraction to finished fabric: resources, yarn production and dyeing, fabric weaving and finishing, waste recycling. Carbon footprint 4,46 kg CO₂ eq /m Water consumption 114,8 liters/m	 UNIVERSITAT POLITÈCNICA DE CATALUNYA BARCELONATECH Escola Superior d'Enginyeries Industrial, Aeroespacial i Audiovisual de Terrassa Study realized in collaboration with UPC Methodology: Life Cycle Analysis. ISO 14040 standard. Database: Own data, Ecoinvent 3.6 database and published data. Functional unit: 1 linear meters, 140 cm width. Calculation methodology: ReCiPe Midpoint (H) 2016 v1.0 ReCiPe Endpoint (H) 2016 v1.04 IPCC 2013 GWP 100a v1.03
Designed and Crafted in Terrassa (Barcelona)	Certificates 	