



stretch • easy stain release

General Information	Specifications	Care
 Composition 88%PES 12%PET REC Width 140 + 4cm Weight 811 gr/m2 ± 5 % 1136 gr/lm ± 5 % Custom code UE: 6005.38.00 USA: 6005.38.00 Laboratory test number IN-00060-2025-1 / 2025 AN 0959 / 601010-01	Seam slippage resistance (mm) Warp: 2 Weft: 1,1 EN ISO 13936/2:2004 Abrasion resistance (End point) EN ISO 12947-2:2016 Tested for decorative use: 25.000 Abrasion resistance (change of aspect: 3000 cycles) 4 EN ISO 12947/4:1998 and EN 14465:2003 (Annex A) Pilling resistance 4 EN ISO 12945/2:2020 Bursting strenght 878,15 Level A EN ISO 13938-2:2019 Lightfastness 5-6 EN ISO 105-B02:1998 and 105 B02/A01:2002 Colour fastness to rubbing Dry: 4-5 Wet: 4-5 EN ISO 105-X12:2002	Washing conditions  Soiling and cleanability 4 FORD FLTM BN 112-08:2005 Dimensional change domestic washing and drying (%) Warp: -3% Weft: -2% EN ISO 3759:2008, EN ISO 6330:2000 and EN ISO 5077:2008 When confectioning or washing the sofa cover with velcro please attach a protective cloth.
		Ignitability BS5852 Source O EN1021-Part 1:2006 CAL TB 117:2013 NFPA 260:2013
Environmental considerations		
 12% recycled yarn 12% GRS recycled PET bottles 88% PES	Life cycle analysis Cradle to gate assessment. From raw material extraction to finished fabric: resources, yarn production and dyeing, fabric weaving and finishing, waste recycling. Carbon footprint 7,55 kg CO₂ eq/m Water consumption 126,31 liters/m	 UNIVERSITAT POLITÈCNICA DE CATALUNYA BARCELONATECH Escola Superior d'Enginyeries Industrial, Aeroespacial i Audiovisual de Terrassa Study realized in collaboration with UPC Methodology: Life Cycle Analysis. ISO 14040 standard. Database: Own data, Ecoinvent 3.6 database and published data. Functional unit: 1 linear meters, 140 cm width. Calculation methodology: ReCiPe Midpoint (H) 2016 v1.0 ReCiPe Endpoint (H) 2016 v1.04 IPCC 2013 GWP 100a v1.03
Designed and Crafted in Terrassa (Barcelona)	Certificates 	