



outdoor • easy stain release • bleach cleanable

General Information	Specifications	Care
 Composition 67%PP 33%PES REC Width 140 + 4cm Weight 436 gr/m2 ± 5 % 610 gr/lm ± 5 % Custom code UE: 5407.73.00 USA: 5407.73.20.60 Laboratory test number IN-01416-2023-1 218352-3	Seam slippage resistance (mm) Warp: 1,90 Weft: 1,30 EN ISO 13936/2:2004 Abrasion resistance (End point) 50.000 EN ISO 12947-2:2016 Abrasion resistance (change of aspect: 3000 cycles) 4 EN ISO 12947/4:1998 and EN 14465:2003 (Annex A) Pilling resistance Pilling 4-5 / Fuzzing 3-4 EN ISO 12945/2:2000 Lightfastness to weather ≥6 EN ISO 105-B04:1997 (1000 hours) Colour fastness to rubbing Wet: 4-5 Dry: 4-5 EN ISO 105-X12:2002 Swimming pool chlorine fastness 4-5 EN ISO 105-E03:1993 Sea water fastness 4-5 EN ISO 105-E02:1996 Urine fastness 4-5 EN ISO 105-E01:1996	Washing conditions  Soiling and cleanability 4 FORD FLTM BN 112-08:2005 Dimensional change domestic washing and drying (%) Warp: -2 Weft: -2 EN ISO 3759:2008, EN ISO 6330:2000 and EN ISO 5077:2008 Bleach cleanable 80% water 20% bleach. In case of mould growth, machine-wash with a mild laundry detergent and add 0,2 liter of household bleach to the first rinse cycle. Wash at 40° C during at least 30 minutes. Use gentle cycle with minimal centrifugation. When confectioning or washing the sofa cover with veloro please attach a protective cloth. This blended fabric has been designed for joint indoor-outdoor use and uses an innovative material reminiscent of natural fiber that renders a rustic character to the fabric. This novel material has been specially developed to produce unique and durable outdoor furniture. During use the fabric may take on the appearance of wool, which is not to be considered a defect, but a desirable characteristic giving this fabric its unique personality.
Environmental considerations		
 33% GRS recycled PET bottles 67% Low impact yarn (PP)	Life cycle analysis Cradle to gate assessment. From raw material extraction to finished fabric: resources, yarn production and dyeing, fabric weaving and finishing, waste recycling. Carbon footprint <i>In process</i> kg CO₂ eq / m - Water consumption <i>In process</i> liters / m -	 UNIVERSITAT POLITÈCNICA DE CATALUNYA BARCELONATECH Escola Superior d'Enginyeries Industrial, Aeroespacial i Audiovisual de Terrassa Study realized in collaboration with UPC Methodology: Life Cycle Analysis. ISO 14040 standard. Functional unit: 1 linear meters, 140 cm width. Database: Own data, Ecoinvent 3.6 database and published data. Calculation methodology: Aware V1.02 ReCiPe Midpoint (H) 2016 v1.04 ReCiPe Endpoint (H) 2016 v1.04 IPCC 2013 GWP 100a v1.03 Software: SimaPro 9.4.0.1
Designed and Crafted in Terrassa (Barcelona)		