





## easy stain release

General Information	Specifications	Care
 <p><b>Composition</b> 53%PET REC 34%PP 7%CO REC 6%OF REC</p> <p><b>Width</b> 140 + 4cm</p> <p><b>Weight</b> 568 gr/m<sup>2</sup> ± 5 % 795 gr/lm ± 5 %</p> <p><b>Custom code</b> UE: 5407.73.00 USA: 5407.73.20.60</p> <p><b>Laboratory test number</b> IN-000947/2025-1</p>	<p><b>Seam slippage resistance (mm)</b> Warp: 2,3 Weft: 2,3 EN ISO 13936/2:2004</p> <p><b>Abrasion resistance (End point)</b> 50.000 EN ISO 12947-2:2016</p> <p><b>Abrasion resistance (change of aspect: 3000 cycles)</b> 3-4 EN ISO 12947/4:1998 and EN 14465:2003 (Annex A)</p> <p><b>Pilling resistance</b> 4 EN ISO 12945/2:2000</p> <p><b>Lightfastness</b> <u>&gt;6</u> EN ISO 105-B02:1998 and 105 B02/A01:2002</p> <p><b>Colour fastness to rubbing</b> Wet: <u>4-5</u> Dry: <u>4-5</u> EN ISO 105-X12:2002</p> <p><b>Notes:</b> This fabric is woven with a bouclé yarn that creates a natural, irregular surface effect. Bouclé fabrics are generally more sensitive to wear effects than flat wovens, and with intensive or prolonged use may take on a more pronounced texture.</p>	<p><b>Washing conditions</b></p>  <p><b>Soiling and cleanability</b> 3 FORD FLT M BN 112-08:2005</p> <p><b>Dimensional change domestic washing and drying (%)</b> Warp: -3% Weft: -2% EN ISO 3759:2008, EN ISO 6330:2000 and EN ISO 5077:2008</p> <p>Bleach cleanable 80% water 20% bleach. In case of mould growth, machine-wash with a mild laundry detergent and add 0,2 liter of household bleach to the first rinse cycle. Wash at 40°C during at least 30 minutes. Use gentle cycle with minimal centrifugation.</p> <p>When confectioning or washing the sofa cover with velcro please attach a protective cloth.</p> <p><b>Ignitability</b></p> <p>BS5852 Source 0 EN1021-Part 1:2006 CAL TB 117:2013 NFPA 260:2013</p> <p>Upon Request: BS5852 Source 1 EN1021-Part 2:2006 BS 7176 Low Hazard UNI 9175 Clase 3IM</p>

## Environmental considerations

 <p><b>66%</b> recycled yarn</p> <p>53% GRS recycled PET bottles 7% Recycled CO 6% Circular yarn from own waste 34% Low impact yarn (PP)</p>	<p><b>Life cycle analysis</b> Cradle to gate assessment. From raw material extraction to finished fabric: resources, yarn production and dyeing, fabric weaving and finishing, waste recycling.</p> <p><b>Carbon footprint</b> <b>4</b> kg CO<sub>2</sub> eq / m</p> <p><b>Water consumption</b> <b>97,42</b> liters / m</p>	 <p><b>UNIVERSITAT POLITÈCNICA DE CATALUNYA BARCELONATECH</b> Escola Superior d'Enginyeries Industrial, Aeroespacial i Audiovisual de Terrassa</p> <p>Study realized in collaboration with UPC</p> <p>Methodology: Life Cycle Analysis. ISO 14040 standard.</p> <p>Functional unit: 1 linear meters, 140 cm width.</p> <p>Database: Own data, Ecoinvent 3.6 database and published data.</p> <p>Calculation methodology: Aware V1.02 ReCiPe Midpoint (H) 2016 v1.04 ReCiPe Endpoint (H) 2016 v1.04 IPCC 2013 GWP 100a v1.03 Software: SimaPro 9.4.0.1</p>
---	--	--

Designed and Crafted  
in Terrassa (Barcelona)

